

## CONTINUOUS SANDWICH PANELS

### Typical Properties of Sintex Sandwich Panels :

Density of PU Foam	40 ± 2 Kg. / Cu. Mtr.
Tensile Strength of PU Foam	4 Kg / Sq. Cm.
Compressive Strength (10% Deformation)	2.1 Kg / Sq. Cm
Thermal Conductivity at 10 Deg C	0.02 W/ M. Deg K
Temperature Range	-80 Deg C to + 100 Deg C
Width	1000 mm
Length for retail	2.5 m / 3 m / 5 m / 6 m
Length for projects	Any tailormade length upto 12 m
Finish	Plain/ Ribbed
Thickness Range 30mm, 40mm, 50mm, 60mm, 75mm 100mm, 150mm	

#### WALLING PANELS

External Facing	0.35 mm TCT/ 0.5 mm TCT/ 0.6 mm TCT	Colour coated steel sheet
Internal Facing	0.45 mm TCT/ 0.5 mm TCT/ 0.6 mm TCT	Colour coated steel sheet

#### ROOFING PANELS

External Facing	0.35 mm TCT/ 0.5 mm TCT/ 0.6 mm TCT	Colour coated steel sheet
Internal Facing	0.45 mm TCT/ 0.5 mm TCT/ 0.6 mm TCT	Colour coated steel sheet OR Aluminium Foil OR Craft Paper

